

Lipid nanoparticle-based gene therapies for osteoarthritis: A review

Jie Li^{1,2}, Jing Wang^{1,2*}, and Qinghao Zhang^{3,4*}

ABSTRACT

Osteoarthritis (OA) remains a leading cause of disability and lacks approved disease-modifying pharmacotherapies, affecting over 500 million people worldwide. Over the past decade, advances in joint biology, molecular research on cartilage and subchondral bone degeneration, and nanomaterial studies for targeted delivery have driven gene therapy strategies for OA. Early clinical studies employing local delivery of anti-inflammatory or anabolic transgenes through adeno-associated virus, helper-dependent adenovirus, or plasmids have demonstrated intra-articular expression and initial safety, establishing regulatory and translational pathways. Recent advances in molecular biology and nanotechnology have enabled the emergence of RNA-based therapies delivered via lipid nanoparticles (LNPs). LNPs, clinically validated through their use in mRNA COVID-19 vaccines, offer a modular and scalable system for nucleic acid delivery. They provide stability for RNA constructs, enhance joint retention, and facilitate penetration into the dense extracellular matrix of cartilage. Preclinical studies have demonstrated that intra-articular administration of LNP-encapsulated small interfering RNAs and messenger RNAs can suppress inflammatory mediators, silence catabolic enzymes, and promote cartilage regeneration. This review summarizes recent studies on the design, optimization, and translational progress of LNP-based RNA therapies for OA, addressing ongoing challenges related to durability, re-dosing, scalability, and immunogenicity. It outlines a roadmap for achieving disease-modifying RNA therapeutics in OA.

Keywords:

Osteoarthritis; Gene therapy; Lipid nanoparticle; Gene delivery

*Corresponding authors:

Jing Wang,
wangjing08@ecust.edu.cn;
Qinghao Zhang,
qiz43@ecust.edu.cn

How to cite this article:

Li, J.; Wang, J.; Zhang, Q.
Lipid nanoparticle-based gene
therapies for osteoarthritis:
A review. *Biomater Transl.*
2026, 7(3), 399-412.

doi: [10.12336/bmt.25.00136](https://doi.org/10.12336/bmt.25.00136)



1. Introduction

Osteoarthritis (OA) is the most common degenerative joint disease and a leading cause of pain and disability in aging populations. Globally, more than 500 million individuals are affected, with prevalence expected to rise further as life expectancy and obesity rates increase.^{1,2} The disease is characterized by the progressive loss of articular cartilage, subchondral bone remodeling, synovial inflammation, and the formation of osteophytes. These structural changes result in pain, stiffness, and impaired mobility, ultimately leading to significant socioeconomic and healthcare burdens. Despite the high prevalence and impact, effective disease-modifying OA drugs (DMOADs) remain elusive.

Currently available treatments are primarily symptomatic. Non-pharmacological core

approaches, including weight management and exercise, remain foundational to effective treatment. Pharmacological treatments such as non-steroidal anti-inflammatory drugs and intra-articular corticosteroids offer short-term relief but do not alter disease progression. Advanced cases often necessitate surgical interventions, including total joint replacement, which is invasive, expansive, and associated with significant risks.³ As shown in **Figure 1**, current OA treatment strategies primarily focus on pain control and functional improvement, rather than targeting the molecular drivers of joint degeneration.

The failure to develop effective DMOADs stems from the multifactorial and heterogeneous nature of OA. Cartilage, subchondral bone, synovium, and meniscus are dynamically interconnected,




Figure 1. Current treatment approaches for osteoarthritis include non-pharmacological interventions, pharmacological treatments, and surgical procedures. While these methods alleviate symptoms, they do not modify disease progression.³ Created in BioRender.com (Qinghao Zhang *et al.*) 2025 <https://BioRender.com/calsoad>.

creating a complex microenvironment that resists mono-therapeutic interventions. The avascular structure and dense extracellular matrix (ECM) of cartilage present formidable barriers to drug penetration and retention. Moreover, systemic drug delivery is hampered by rapid clearance, poor joint-specific bioavailability, and the risk of off-target toxicity.⁴ These challenges highlight the urgent need for novel delivery systems capable of transporting therapeutic molecules directly into the joint and maintaining their activity *in situ*.⁵

Against this backdrop, nucleic acid-based therapeutics—particularly RNA-based modalities—have emerged as a promising frontier. Messenger RNAs (mRNAs), small interfering RNAs (siRNAs), and circular RNAs (circRNAs) can modulate gene expression with high precision, allowing suppression of catabolic mediators, blockade of inflammatory pathways, and enhancement of anabolic signaling.^{6,7} Currently, RNA therapeutics can target an increasing number of genes, expanding the therapeutic landscape for OA.

The clinical validation of lipid nanoparticle (LNP)-based RNA delivery in vaccines has catalyzed their exploration in musculoskeletal disorders.^{8,9} LNPs encapsulate RNA, protecting it from nuclease degradation and facilitating cellular uptake, while enabling controlled and localized expression. Recent preclinical work demonstrates that intra-articular injection of LNPs can silence inflammatory cytokines, inhibit matrix metalloproteinases (MMPs), and promote cartilage repair.¹⁰ Moreover, strategies combining LNPs with hydrogel depots or engineering circRNA payloads have enhanced retention times and improved therapeutic durability.^{11,12} These

findings underscore the potential of LNP-based RNA delivery systems to shift OA treatment from symptomatic management to disease modification.

2. Pathophysiological mechanisms of OA

OA is increasingly recognized as a multifactorial disease characterized not only by cartilage degradation but also by a complex interplay of pathological events involving the synovium, subchondral bone, and periarticular tissues.^{13,14} Unlike inflammatory arthritides such as rheumatoid arthritis, which are primarily driven by systemic immune dysregulation, OA develops insidiously through biomechanical stress, cellular senescence, low-grade inflammation, and metabolic dysfunction. This multifaceted and synergistic pathophysiology underscores the need for multi-targeted therapeutic strategies, making programmable RNA-based therapeutics delivered via LNPs particularly attractive, as they can be designed to modulate multiple pathogenic pathways simultaneously.^{1,15,16}

2.1. Cartilage degeneration and ECM breakdown

The primary hallmark of OA is the progressive deterioration of articular cartilage, a highly specialized tissue composed mainly of type II collagen and aggrecan.¹⁷ Chondrocytes are the sole resident cells responsible for maintaining cartilage homeostasis, balancing anabolic processes that synthesize ECM proteins with catabolic mechanisms that degrade them. In OA, this balance is disrupted, favoring catabolism. MMPs, especially MMP-13, aggrecanases such as disintegrin, and metalloproteinase with thrombospondin type 1 motif (ADAMTS)-4 and ADAMTS-5, are markedly upregulated, driving collagen and proteoglycan degradation.^{18–20} Their expression is stimulated by pro-inflammatory cytokines, notably interleukin (IL)-1 β and tumor necrosis factor- α (TNF- α).²¹

Traditional pharmacological attempts to inhibit MMPs have failed due to off-target toxicity and insufficient selectivity. In contrast, RNA-based approaches, such as siRNAs, offer a promising strategy to specifically silence MMP-13 or ADAMTS-5 expression. Preclinical studies have demonstrated that targeted delivery of siRNAs against MMP-13, encapsulated in nanoparticles, can significantly attenuate cartilage destruction in rodent OA models.^{22,23}

2.2. Inflammatory pathways and synovial activation

OA is now recognized as a low-grade inflammatory disease, characterized by synovial tissue infiltration with macrophages and activation of innate immune signaling. This creates a pro-inflammatory milieu characterized by elevated levels of IL-1 β , TNF- α , and IL-6, which amplify catabolic cascades in chondrocytes and sensitize nociceptive neurons, as illustrated

¹The State Key Laboratory of Bioreactor Engineering, Department of Material Science and Engineering, East China University of Science and Technology, Shanghai, China; ²Department of Material Science and Engineering, Frontiers Science Center for Materiobiology and Dynamic Chemistry, East China University of Science and Technology, Shanghai, China; ³Department of Systems Biology, Innovative Center of RNA Medicine, School of Life Sciences, Southern University of Science and Technology, Shenzhen, Guangdong, China; ⁴Guangming Advanced Research Institute, Southern University of Science and Technology, Shenzhen, Guangdong, China

in **Figure 2**. Central to this process is the nuclear factor kappa B (NF- κ B) pathway. The activation of NF- κ B promotes the transcription of pro-inflammatory cytokines, chemokines, and matrix-degrading enzymes, perpetuating a vicious cycle of joint destruction and pain.²⁴ Importantly, synovial inflammation and the resulting cytokine release directly exacerbate cartilage catabolism and subchondral bone remodeling, illustrating the critical crosstalk between joint tissues that necessitates therapeutic strategies capable of intervening at multiple levels.

Another critical pathway is the Janus kinase/signal transducer and activator of transcription (JAK/STAT), which regulates both inflammatory and catabolic genes. Targeting these intracellular signaling cascades using siRNAs or antisense oligonucleotides has shown promise in preclinical models of OA. For example, RNA therapeutics directed against NF- κ B subunits have been shown to reduce synovial hyperplasia and protect cartilage in rodent studies.^{25,26} In summary, the low-grade inflammatory milieu in OA, driven by synovial activation and key signaling pathways such as NF- κ B and JAK/STAT, is a central driver of disease progression and pain, presenting a compelling target for LNP-encapsulated RNA inhibitors.

2.3. Subchondral bone remodeling

Subchondral bone changes are integral to OA pathogenesis. The early stages are characterized by increased bone remodeling and bone marrow lesions, followed by sclerosis and the formation of osteophytes. These alterations not only contribute to mechanical stress on cartilage but also influence biochemical signaling within the joint. The Wnt/ β -catenin pathway plays a pivotal role, with overactivation driving osteophyte formation and insufficient activity leading to bone fragility. RNA-based

therapeutics offer the opportunity to modulate this pathway with high specificity. For example, mRNA delivery of Wnt antagonists or siRNA-mediated silencing of sclerostin has been investigated as a strategy to restore homeostasis in subchondral bone remodeling.²⁷

2.4. Anabolic, reparative, and microenvironment-modulating pathways

To achieve long-term disease modification, effective therapeutic strategies must extend beyond suppressing catabolism and inflammation to actively promoting anabolic repair and addressing the broader pathologic joint microenvironment. Transforming growth factor- β (TGF- β) and bone morphogenetic proteins are among the most potent regulators of cartilage repair, stimulating chondrocyte survival and matrix synthesis. However, dysregulated TGF- β signaling in aged or osteoarthritic joints can paradoxically drive osteophyte formation and synovial fibrosis, highlighting the importance of precise modulation.^{28,29} Recent studies have highlighted insulin-like growth factor 1 (IGF1) and fibroblast growth factor 18 (FGF18) as particularly promising anabolic targets. LNP-encapsulated mRNA encoding IGF1 or FGF18 has been shown in animal models to enhance matrix regeneration and restore cartilage structure more effectively than recombinant protein injections, owing to sustained intra-articular expression.^{30,31} The OA microenvironment is further shaped by epigenetic regulation, where microRNAs (miRNAs) such as miR140, miR146a, and miR27b fine-tune cartilage homeostasis. Their dysregulation contributes to OA pathogenesis, making miRNA mimics or inhibitors delivered through LNPs a viable strategy to restore regulatory networks.³²⁻³⁴ Emerging roles for long

Molecular mediated pathways in OA microenvironment




Figure 2. The NF- κ B and JAK/STAT activation pathways in OA synovium, highlighting potential RNA therapeutic targets for modulating inflammation and catabolism.^{25,26} Created in BioRender.com (Qinghao Zhang et al.). 2025 <https://BioRender.com/041eagd>.

Abbreviations: JAK: Janus kinase; NF- κ B: Nuclear factor kappa B; OA: Osteoarthritis; STAT: Signal transducer and activator of transcription.

non-coding RNAs (lncRNAs) and circRNAs further expand the therapeutic landscape for microenvironment modulation.^{35,36}

Finally, pain, a defining feature of the OA microenvironment mediated by factors such as nerve growth factor (NGF), represents a critical therapeutic target. While anti-NGF antibodies show efficacy, RNA-based approaches targeting NGF or downstream mediators offer potential for localized, precisely tunable analgesia with reduced systemic side effects.³⁷⁻³⁹ Thus, the joint microenvironment presents multiple interconnected targets—anabolic, epigenetic, and nociceptive—for LNP-based RNA therapies aiming to achieve comprehensive disease modification. Collectively, the pathophysiological landscape of OA is complex and interconnected, involving cartilage breakdown, inflammation, bone changes, pain signaling, and epigenetic dysregulation. This underscores the rationale for employing versatile LNP-encapsulated RNA therapeutics that can be co-formulated or sequentially administered to target multiple pathways for enhanced efficacy.

3. Advances in gene delivery systems for OA

The efficacy of RNA-based therapeutics in OA hinges on the development of efficient and safe delivery systems that can overcome the unique anatomical and biological barriers of the joint. Over the past two decades, multiple gene delivery platforms have been investigated, including viral vectors, non-viral biologically derived systems, and biomaterial-based carriers, as illustrated in **Figure 3**. While viral vectors initially dominated the field due to their high transduction efficiency, concerns regarding safety, immunogenicity, and re-dosing limitations have spurred the transition toward non-viral systems. Among these, LNPs have emerged as the most clinically validated and versatile vehicles, benefiting from rapid progress catalyzed by the COVID-19 mRNA vaccine experience.^{16,40}

3.1. Viral vectors

Adeno-associated viruses (AAVs) have been widely explored in musculoskeletal research due to their ability to transduce

both dividing and non-dividing cells, low pathogenicity, and relatively stable expression. Preclinical studies have demonstrated that intra-articular injection of AAVs encoding anti-inflammatory proteins, such as IL-1 receptor antagonist, or anabolic growth factors, like IGF1, leads to local protein expression and symptomatic improvement in OA models.⁴¹ However, limitations quickly became apparent. Immune responses against AAV capsids restricted the feasibility of repeated dosing, a critical issue given the chronic nature of OA. In addition, the restricted packaging capacity of AAVs limited their ability to deliver complex constructs, such as multicistronic RNAs or large circRNAs.

3.2. Non-viral biologically derived systems

Non-viral biologically derived carriers, such as engineered bacteria or extracellular vesicles (EVs), have been applied in gene delivery.^{42,43} For example, attenuated *Escherichia coli* strains have been used to deliver plasmids encoding therapeutic genes.^{44,45} It is important to note that EVs, including exosomes and microvesicles, exhibit substantial heterogeneity. Different EV subtypes (e.g., based on cellular origin or isolation method) can have significantly different RNA loading capacities, cartilage penetration efficiencies, and immunogenic profiles, which must be carefully considered when comparing them to synthetic vectors such as LNPs. These systems benefit from their intrinsic cell-penetrating properties and potential for delivering large payloads. However, their translation to OA therapy remains limited due to significant concerns regarding safety, unpredictability of host responses, and regulatory complexity.

3.3. Polymer-based nanoparticles

Polymeric nanoparticles represent another important non-viral platform. Cationic polymers such as polyethyleneimine (PEI) and chitosan have been tested for intra-articular delivery of plasmid DNA and siRNAs targeting catabolic enzymes.⁴⁶ For instance, PEI-condensed siRNA against MMP-13 reduced cartilage matrix degradation in OA.⁴⁷ More recently, biodegradable poly β -amino esters have been engineered to mitigate the cytotoxicity associated with earlier cationic polymers while maintaining efficient nucleic acid delivery.⁴⁸⁻⁵⁰ Nevertheless, challenges remain regarding the reproducibility of synthesis, scalability, and ensuring penetration into the dense cartilage ECM.

3.4. LNPs development in clinical settings

The breakthrough in LNP technology for RNA delivery has redefined the gene therapy landscape.⁵¹ Clinically validated through their use in mRNA vaccines against SARS-CoV-2, LNPs provide a scalable, safe, and versatile platform well-suited for intra-articular applications. Structurally, LNPs consist of ionizable lipids, cholesterol, helper lipids, and polyethylene glycol (PEG)-conjugated lipids, which together encapsulate and protect RNA from degradation, facilitate endosomal escape, and enable controlled release. Unlike viral vectors, LNPs allow repeat dosing without significant risk of neutralizing immune responses, a critical advantage for chronic conditions such as OA.^{2,16,52}




Figure 3. Overview of viral vectors, non-viral platforms, and lipid-based nanoparticle gene delivery systems investigated for OA, along with their respective advantages and limitations.^{16,41,46} Created in BioRender.com (Qinghao Zhang *et al.*) 2025 <https://BioRender.com/jnyr8vx>.

Abbreviations: AAV: Adeno-associated virus; EV: Extracellular vesicles; OA: Osteoarthritis.

In preclinical OA models, intra-articular administration of siRNA-LNPs targeting catabolic enzymes such as ADAMTS-5 has been shown to reduce cartilage erosion and improve joint function.^{53,54} Similarly, mRNA-based LNPs encoding IGF1 have been demonstrated to stimulate anabolic signaling and enhance cartilage repair, with superior outcomes compared to recombinant protein injections due to sustained local expression.⁵⁵⁻⁵⁷ Recent studies have further demonstrated the potential of circRNA/LNP formulations, which combine the stability of circRNAs with the delivery efficiency of LNPs, thereby enabling prolonged therapeutic activity in OA joints.⁵⁸⁻⁶⁰ **Figure 4** provides a comparative overview of these delivery systems.

3.5. Transition from viral to LNP platforms

The trajectory from viral vectors to LNP-based systems reflects the broader shift in gene therapy for OA.⁶¹ As summarized in **Table 1**, each delivery platform possesses distinct advantages and limitations. Viral systems provided the initial proof of

concept for localized gene expression, but were hindered by immune responses and re-dosing barriers.⁶²⁻⁶⁴

LNPs now combine the scalability, safety, and efficiency required for clinical translation, representing the most promising platform for achieving sustained, tunable RNA expression in OA joints. Importantly, the modularity of LNPs allows for future integration with targeting ligands, responsive hydrogels, and combinatorial RNA payloads to address the multifactorial pathology of OA.⁶⁰ Among RNA-based therapeutics, circRNAs have recently emerged as a particularly promising approach for OA treatment. **Figure 5** illustrates the mechanisms of the LNP-based circRNA delivery system in chondrocytes.

In summary, while viral vectors pioneered gene therapy for OA and non-viral alternatives explored safer options, LNPs have emerged as the leading platform, successfully balancing efficacy, safety, manufacturability, and re-dosing potential, thereby paving the way for clinical translation of RNA therapeutics.




Figure 4. Lipid nanoparticle (LNP) structure and mechanism of intra-articular RNA delivery, showing LNP administration, cartilage penetration, and cellular uptake.^{53,55,58} Created in BioRender.com (Qinghao Zhang *et al.*) 2025 <https://BioRender.com/q601jp8>.

Table 1. Comparison of major nucleic acid delivery platforms

Delivery platform	Advantages	Disadvantages
Lipid nanoparticles	Low immunogenicity; high engineering flexibility; suitable for repeat dosing; large payload capacity; scalable manufacturing	Efficiency, stability, and tissue targeting can be suboptimal
Adeno-associated virus	Low immunogenicity; tissue tropism; long-term/durable transgene expression	Small cargo capacity (~4.7 kb); can elicit immune responses; delayed onset of expression; high production costs
Lentivirus	Transduces both dividing and non-dividing cells; larger cargo capacity than adeno-associated virus	Random integration risk (insertional mutagenesis); high immunogenicity
Polymeric nanoparticles	High biocompatibility; tunable structure; low immunogenicity	Lower transfection efficiency; instability; complex <i>in vivo</i> behavior
Extracellular vesicles	High biocompatibility; low immunogenicity; high stability	Complex manufacturing and isolation; rapid hepatic clearance; significant heterogeneity among extracellular vesicle subtypes




Figure 5. CircRNA-based LNP delivery system in chondrocytes.^{53,59,60} Created in BioRender.com (Qinghao Zhang *et al.*) 2025 <https://BioRender.com/mk0o8a7>.

Abbreviations: CircRNA: Circular RNA; IRES: Internal ribosome entry site; LNP: Lipid nanoparticle.

4. Preclinical progress in LNP-based RNA therapeutics for OA

Building upon the clinical success of LNP-based mRNA vaccines, researchers have adapted this technology to address the unique challenges of intra-articular delivery.^{65,66} Recent preclinical studies have demonstrated the feasibility of using LNPs to deliver a range of RNA payloads, including siRNAs, mRNAs, and circRNAs, to modulate key pathogenic pathways in OA, resulting in significant structural and symptomatic improvements.⁶⁷⁻⁷¹

Recent preclinical studies have demonstrated the efficacy of LNP-based mRNA delivery for the treatment of OA. As shown in **Figure 6**, intra-articular injection of LNP-encapsulated FGF18-modified mRNA significantly enhanced FGF18 expression in mouse joints, activating the forkhead box O3a-mediated autophagy pathway to alleviate chondrocyte senescence and cartilage degeneration. Furthermore, optimizing formulation parameters such as the water-to-ethanol ratio, nitrogen-to-phosphorus ratio, PEG percentage, and dialysis buffer concentration proved crucial for enhancing the accumulation and retention of LNPs within the joint cavity, as evidenced by luciferase mRNA imaging.⁷¹

4.1. LNP-delivered siRNAs targeting catabolic pathways

Silencing catabolic enzymes represents a major focus in LNP-delivered siRNA therapeutic strategies for OA. MMP-13 and aggrecanases (e.g., ADAMTS-4 and ADAMTS-5) are among the most critical mediators of ECM degradation. Recent studies have demonstrated that the intra-articular administration of LNP-encapsulated siRNAs targeting MMP-13 in rodent models resulted in a significant reduction in cartilage erosion and osteophyte formation, accompanied by improved gait and mobility scores compared to controls. For example, Zhao *et al.*⁶⁷ reported a novel LNP-based siRNA formulation targeting fibroblast activation protein (FAP), which is upregulated in

senescent chondrocytes. FAP-siRNA/LNP complex effectively reduced the senescent chondrocyte burden, suppressed NF- κ B-driven senescence-associated secretory phenotype, and preserved cartilage and subchondral bone integrity.^{68,69}

4.2. LNP-delivered mRNAs promoting cartilage regeneration

An equally promising avenue involves the delivery of mRNAs encoding anabolic and reparative factors. *FGF18* and *SOX9* are among the most widely studied genes.^{30,70} A study introduced a cartilage-optimized LNP system engineered for intra-articular mRNA delivery, which achieved higher joint-specific expression of *FGF18* compared to conventional LNPs while minimizing off-target liver uptake.⁷¹ Optimization of the untranslated regions (UTRs) and nucleoside modifications of *FGF18* mRNA has been shown to extend intra-articular expression to nearly 1 week.⁷¹⁻⁷³ This formulation effectively reduces chondrocyte senescence and sustains cartilage homeostasis.³⁰

4.3. circRNA-LNP delivery systems

Recently, circRNAs have emerged as an innovative RNA modality for OA therapy due to their structural stability and multifunctionality.⁷⁴ As illustrated in **Figure 7**, circRNAs can be engineered for high-efficiency protein translation through optimized UTRs, internal ribosome entry site elements, and N6-methyladenosine modifications (**Figure 7A**), or for sequence-specific interference, functioning as miRNA sponges, protein decoys, or antisense molecules (**Figure 7B**).

Their covalently closed loops confer resistance to exonuclease degradation, which may offer advantages within the inflammatory environment of OA.⁷⁵ Moreover, circRNAs act as miRNA sponges and protein scaffolds, providing multilayered regulation of pathogenic pathways.⁷⁶

In a previous study, a circRNA construct encoding a super-repressor of NF- κ B was delivered via LNPs, achieving significant




Figure 6. Schematic diagram of the LNP delivery system for osteoarthritis therapy and *in vivo* experimental results. (A) Intra-articular delivery of LNP-encapsulated FGF18 modified mRNA for osteoarthritis therapy. Injection of LNP-FGF18 into the mouse joint cavity significantly increased FGF18 expression *in vivo*, activating the FOXO3a-mediated autophagy pathway and protecting cartilage by attenuating chondrocyte senescence and degeneration. (B) Schematic illustration of the nanoparticle preparation method. (C) Illustration of enhanced accumulation of luciferase-mRNA LNPs in cartilage cavity through optimization of the W/O ratio, the N/P ratio, the percentage of PEG, and the concentration of dialysis buffer. (D) Size, zeta potential, and bioluminescence imaging of ICR mice ($n = 3$) after intra-articular injection of LNP-luciferase mRNA (2 μ g mRNA) in different formulations. The fluorescent scale bar unit is photons/sec/cm²/sr, with a radiance scale of 1.0×10^7 – 2×10^8 . Data were represented as mean $\pm$ standard error of the mean. Statistical significance was calculated via one-way analysis of variance, followed by Dunnett's multiple comparisons test (* $p < 0.05$, ** $p < 0.01$, and *** $p < 0.001$).⁷¹ Reprinted with permission from Sun *et al.*⁷¹ Copyright © 1999–2025 John Wiley & Sons, Inc.

Abbreviations: FOXO3a: Forkhead box O3a; ICR: Institute of Cancer Research; LNP: Lipid nanoparticle; mRNA: Messenger RNA; N/P: Nitrogen-to-phosphorus; PEG: Polyethylene glycol; W/O: Water-to-ethanol.




Figure 7. Key components of engineered circRNAs for various purposes. (A) Engineered circRNAs for protein translation. Design of a 5' UTR to improve the translational efficiency of circRNAs. 5' UTR, including elements such as poly(A) binding protein motifs and eIF4G-recruiting aptamers (indicated in yellow), which increase circRNA translation by recruiting eIF4G, a key scaffold protein in the translation-initiation step (step 1). Incorporation of an IRES, such as CVB3 IRES, enables cap-independent translation initiation of circRNAs. Short IRES elements, containing a complementary 18S sequence or a stem loop of approximately 40–60 nucleotides, can also initiate circRNA translation. Adding eIF4G-recruiting aptamers at both the distal and proximal positions of the CVB3 further increases the translation efficiency of circRNAs (step 2). m⁶A modification drives circRNA protein translation by recruiting the cytoplasmic m⁶A reader YTHDF3, which interacts with the 40S and 60S ribosome subunits, and abrogates circRNA immunity without activating RIG-I innate immune signaling (step 3). The protein-coding sequence of circRNA includes a start codon, an ORF, and a stop codon. circRNAs encode proteins via canonical linear ORF translation, stop codon bypass, or rolling circle translation (step 4). Incorporation of the human α -globin 3' UTR, which interacts with cytoplasmic poly(C) binding proteins forming an α -complex, has been reported to enhance circRNA translation efficiency (step 5). (B) Engineered circRNAs for sequence-based interference. miRNA sponges (circmiR) were engineered with six miR-132 and six miR-212 binding sites prepared by a 6-nucleotide spacer to inhibit miRNA activity (step 1). Protein sponges: artificial hnRNPL sponge circRNAs containing CA-rich sequence clusters modulate pre-mRNA splicing via hnRNPL sequestration (step 2). Antisense circRNAs: through base-pairing, synthetic circRNAs can bind with DNA, pre-mRNA, or mRNA to regulate gene activity (step 3). Guide circRNAs can be used for genome and transcriptome editing (step 4).⁷⁶ Reprinted with permission from Cao *et al.*⁷⁶ Copyright© 2025 Springer Nature Limited.

Abbreviations: ADAR: Adenosine deaminases acting on RNA; circRNA: Circular RNA; circmiR: Circular RNA microRNA sponge; CVB3: Coxsackievirus B3; eIF4G: Eukaryotic initiation factor 4G; hnRNPL: Heterogeneous nuclear ribonucleoprotein L; IRES: Internal ribosome entry site; m⁶A: N⁶-methyladenosine; MCP: MS2 coat protein; nCas12a: Cas12a nickase; ORF: Open reading frame; RIG-I: Retinoic acid-inducible gene I; RT: Reverse transcriptase; UTR: Untranslated region; YTHDF3: YT521-B homology domain family 3.

reductions in inflammatory mediator production and cartilage degradation.⁶⁰ Chen *et al.*⁷⁷ also reported a double-stranded circRNA aptamer-based therapy for OA by inhibiting protein kinase R activation in a destabilization of the medial meniscus mouse model, achieving notable *in vivo* anti-inflammatory effects. Additionally, circRNA/LNP formulations loaded within hydrogels enabled controlled release and prolonged bone regeneration.⁷⁸ Thus, circRNA/LNP systems achieve prolonged therapeutic effects without increasing dosing frequency, aligning well with the long-term treatment needs of OA.

The preclinical progress across these RNA modalities demonstrates the remarkable versatility of LNPs. Whether silencing deleterious genes, expressing therapeutic proteins, or employing multifunctional circRNAs, LNP-based delivery has shown consistent promise in modifying OA disease progression in animal models, paving the way for future clinical applications.

5. Design and optimization of LNPs for intra-articular delivery

The design and optimization of LNP platforms for OA therapy require strategies tailored to the specific biological and mechanical challenges of the intra-articular environment.^{42,74} Unlike systemic drug delivery, which benefits from vascular circulation, intra-articular administration must overcome rapid clearance through synovial fluid turnover, the dense ECM of cartilage, and the need for repeated dosing over the chronic course of disease.⁷⁹ Consequently, refinements in both the molecular composition and physicochemical properties of LNPs have been central to recent progress in RNA-based OA therapeutics.

At the structural level, the performance of LNPs is influenced by a balance of four principal components: ionizable lipids, cholesterol, helper lipids, and PEG-conjugated lipids. Ionizable lipids form the functional core of the LNP. Their unique pH-responsive chemistry enables neutral charge at physiological conditions, reducing cytotoxicity, while acquiring a positive charge in the acidic environment of the endosome to mediate electrostatic interactions with endosomal membranes and promote cytoplasmic release of RNA payloads. Modifications in head-group structure, linker biodegradability, and tail saturation have significantly improved RNA encapsulation efficiency and chondrocyte transfection in preclinical models.^{80,81} Cholesterol contributes both rigidity and fusogenicity to the bilayer, enhancing intracellular trafficking and endosomal escape.^{82,83} Helper lipids such as distearoylphosphatidylcholine support membrane integrity under the mechanical and enzymatic stresses of the joint. PEG-conjugated lipids provide colloidal stability and prevent aggregation, although excessive PEGylation can impair cartilage penetration and cellular uptake. Recent work introducing biodegradable PEG-conjugate lipids has mitigated the risk of anti-PEG immune responses, supporting safe re-dosing in chronic indications such as OA.^{84,85}

Furthermore, recent novel designs of ionizable lipids, featuring optimized head-group pKa, biodegradable linkers (e.g., ester-based), and tailored tail saturation, are pushing the boundaries of RNA encapsulation efficiency, chondrocyte transfection potency, and *in vivo* safety profiles.^{86,87} While

composition defines the baseline performance, engineering strategies have been essential for addressing the barriers of intra-articular delivery. Bio-adhesive coatings, including hyaluronic acid (HA) and chitosan, have been applied in joint models; HA-coated LNPs achieved prolonged joint retention, enhanced chondrocyte uptake, and reduced cartilage degradation compared to unmodified formulations.^{88,89} Particle size optimization and surface charge modulation further refine delivery efficiency. While strongly cationic formulations risk inducing cytotoxicity and synovial inflammation, slightly positive charges facilitate ECM binding and deeper penetration without compromising safety.⁹⁰

Chemical innovations have further improved localization and durability. Cholesterol analogues have been incorporated to increase hydrophobic interactions with cartilage ECM. In murine OA models, cholesterol-functionalized siRNA/LNPs targeting MMP-13 exhibited prolonged intra-cartilage retention and significant suppression of ECM degradation.⁹¹ Attaching matrix-penetrating peptides to LNP surfaces also enabled more uniform distribution into deeper cartilage layers, resulting in more consistent chondrocyte transfection and improved histological protection.^{92,93}

Despite these advances, the issue of rapid synovial clearance remains. To address this, LNPs have been integrated with hydrogel-based depots, creating hybrid systems that allow sustained release. Natural polymers, such as HA, and synthetic PEG hydrogels have been employed to embed LNPs, allowing RNA payloads to be released gradually over several weeks. In rabbit OA models, hydrogel-LNP hybrids significantly prolonged intra-articular retention and improved cartilage preservation compared with LNPs alone.^{94,95} Furthermore, inflammation-responsive hydrogels embedding IL-1 receptor antagonist mRNA/LNPs have been developed to achieve on-demand release under elevated cytokine conditions, ensuring that therapeutic expression aligns with disease flares and minimizes unnecessary exposure.^{88,96}

Collectively, the optimization of LNP design can advance RNA therapy for OA toward clinical viability via composition, surface engineering, and integration with advanced biomaterials. By ensuring effective encapsulation, prolonged retention, deep tissue penetration, and compatibility with repeated dosing, these systems address the major barriers of intra-articular RNA delivery and establish a strong foundation for the clinical development of DMOADs.

5.1 Hydrogel-LNP hybrid systems for sustained release

Although LNPs offer efficient encapsulation and cellular delivery, rapid synovial clearance limits their therapeutic window.⁹⁷ Hybrid hydrogel/LNP systems have been developed to address this issue. HA-based or gelatin methacryloyl-based hydrogels embedding RNA/LNPs can achieve extended retention in joints, reduce ECM loss, and improve cartilage morphology for longer periods compared with free LNPs.^{58,60,98}

Similarly, a cholesterol-modulated hydrogel system co-delivering siRNA-LNPs against cholesterol 25-hydroxylase modulated chondrocyte lipid metabolism and enhanced

anabolic activity. In OA models, this strategy reduced MMP expression, increased SRY-box transcription factor 9 and collagen II levels, and recruited mesenchymal stem cells for cartilage regeneration.⁵⁴ Furthermore, advanced “smart” hydrogels that respond to environmental cues (e.g., pH, reactive oxygen species) have been engineered to achieve on-demand release of LNP/RNA payloads during disease flares, thereby enhancing therapeutic specificity.

5.2. Smart environment-responsive hydrogel-LNP hybrid systems

The integration of LNPs with smart, microenvironment-responsive hydrogels represents a cutting-edge strategy to

overcome the challenge of rapid synovial clearance and achieve on-demand drug release.

An exemplary system (circ-srIkB α @LNP-SHC) is depicted in **Figure 8**. In this sophisticated design, circRNA-loaded LNPs were surface-modified with both a cartilage-affinity peptide and an anti-FAP single-chain variable fragment for dual targeting of chondrocytes and fibroblast-like synoviocytes (**Figure 8A**). These targeted LNPs were then encapsulated within a silk fibroin composite hydrogel cross-linked via an MMP13-specific substrate peptide. This design ensures that the therapeutic LNPs are released specifically in response to elevated MMP13 levels found in the inflammatory OA joint,




Figure 8. Design and therapeutic evaluation of an environmentally responsive nanoparticle-hydrogel system (circ-srIkB α @LNP-SHC) for the treatment of OA. (A) Schematic diagram of the environment-responsive drug delivery system (circ-srIkB α @LNP-SHC) for OA treatment: (i) circ-srIkB α , which inhibits nuclear translocation of P65, was encapsulated into LNPs. The LNPs were surface-modified with a cartilage-affinity peptide and an anti-FAP single-chain variable fragment to enable specific targeting of chondrocytes and FLS, respectively; (ii) an MMP13-specific substrate peptide was used to cross-link SHC composite hydrogels with circ-srIkB α @LNP, allowing for environmentally responsive release of circ-srIkB α @LNP proportional to MMP13 levels, thereby establishing an intelligent, environment-responsive drug delivery system; and (c) intra-articular injection of circ-srIkB α @LNP-SHC effectively inhibits NF- κ B signaling, reduces secretion of MMPs and inflammatory factors, preserves the extracellular matrix, maintains joint microenvironment homeostasis, and mitigates OA progression. (B) Therapeutic effect of circ-srIkB α @LNP-SHC on human OA cartilage explants: (i) Schematic diagram of the procedures for harvesting and treating human OA cartilage explants. Cartilage explants were harvested from the medial condyle of the femur of OA patients undergoing total knee arthroplasty; (ii-iv) representative images of (ii) Safranin O-fast green, (iii) H&E, and (iv) Masson's trichrome staining in IL-1 β -maintained explants treated with SHC or circ-srIkB α @LNP-SHC (scale bar: 1,000 μ m; magnification: 40 $\times$). Copyright © 2025 The Authors Published by Elsevier B.V. Reprinted with permission of the Li *et al.*

Abbreviations: FAP: Fibroblast activation protein; FLS: Fibroblast-like synoviocytes; H&E: Hematoxylin and eosin; IL: Interleukin; LNP: Lipid nanoparticle; MMP: Matrix metalloproteinase; NF- κ B: Nuclear factor κ -light-chain-enhancer of activated B cells; OA: Osteoarthritis; SHC: Silk fibroin hydrogel composite.

establishing a positive feedback loop for intelligent drug release. Upon intra-articular injection, this system effectively inhibits NF- κ B signaling, reduces inflammatory mediators and matrix-degrading enzymes, and preserves the ECM, thereby mitigating OA progression. Importantly, the efficacy of this system was validated not only in animal models but also in human OA cartilage explants, where it significantly reduced MMP13 expression and enhanced the synthesis of key cartilage components, including type II collagen and aggrecan (Figure 8B), demonstrating its strong clinical translation potential.⁶⁰

6. Conclusions

LNP-based RNA therapeutics represent a transformative strategy for OA, offering a strategy to achieve disease modification beyond symptomatic relief.⁹⁹ By enabling localized, programmable, and multifaceted regulation of inflammatory, catabolic, and anabolic pathways, LNP platforms have demonstrated strong preclinical efficacy in preserving cartilage integrity, modulating subchondral bone remodeling, and alleviating pain. The integration of diverse RNA modalities further broadens the therapeutic landscape, highlighting the versatility of LNP systems in addressing the multifactorial nature of OA pathogenesis.

Despite these advances, several critical challenges must be addressed before RNA/LNP therapeutics can be successfully translated into clinical applications. First, the durability of therapeutic effects remains essential, as the chronic course of OA necessitates long-term modulation of pathogenic pathways. Achieving safe and effective re-dosing regimens is equally important, given the need for sustained treatment without triggering adverse immune responses. Finally, the potential for immunogenicity, both from RNA constructs and from repeated LNP administration, necessitates careful optimization of lipid chemistry and RNA design to minimize unintended immune activation.

To accelerate clinical translation, strategic approaches should include the design of cartilage-targeting LNPs with enhanced penetration and retention, and the incorporation of bioresponsive release systems to align therapeutic activity with disease flares. Collaborative frameworks integrating materials science, molecular biology, and clinical orthopedics for gene therapeutics in OA are essential to achieve safe, effective, and truly disease-modifying interventions that can not only alleviate symptoms but also alter the course of joint degeneration. Lipid chemistry, RNA engineering, and intra-articular delivery strategies hold the potential to fundamentally redefine the therapeutic paradigm for OA, shifting treatment from symptomatic management to durable structural restoration and functional recovery.

Acknowledgement

The authors acknowledge the use of Biorender (<https://app.biorender.com/>) in the creation of some of the illustrations used in the manuscript.

Financial support

This work was supported in part by the Key Program of the National Natural Science Foundation of China (No. 32230059) and Key Research and Development Plan of Shandong Province (2023CXPT103).

Conflicts of interest statement

The authors declare that they have no conflicts of interest.

Author contributions

Conceptualization: QZ; Writing—original draft: All authors; Writing review & editing: QZ and JW. All authors have read and approved the final version of the manuscript for publication.

Ethics approval and consent to participate

Not applicable.

Consent for publication

Not applicable.

Availability of data

Not applicable.

Open access statement

This is an open-access journal, and articles are distributed under the terms of the Creative Commons Attribution-Non-Commercial-Share Alike 4.0 License, which allows others to remix, tweak, and build upon the work noncommercially, as long as appropriate credit is given and the new creations are licensed under the identical terms.

References

- Hunter DJ, Bierma-Zeinstra S. Osteoarthritis. *Lancet*. 2019;393(10182):1745-1759. doi: 10.1016/S0140-6736(19)30417-9
- Tang S, Zhang C, Oo WM, et al. Osteoarthritis. *Nat Rev Dis Primers*. 2025;11(1):10. doi: 10.1038/s41572-025-00594-6
- Liang W, Zhou C, Bai J, et al. Current advancements in therapeutic approaches in orthopedic surgery: A review of recent trends. *Front Bioeng Biotechnol*. 2024;12:1328997. doi: 10.3389/fbioe.2024.1328997
- Kim HJ, Le ND, Oh HJ, et al. Lipid nanoparticle-assisted mRNA therapy for cancer treatment. *Appl Phys Rev*. 2025;12(3):031328. doi: 10.1063/5.0247029
- Alfutaiani AS, Alharbi NK, Alahmari AS, Alqabbani AA, Aldayel AM. Exploring the landscape of Lipid Nanoparticles (LNPs): A comprehensive review of LNPs types and biological sources of lipids. *Int J Pharm X*. 2024;8:100305. doi: 10.1016/j.ijpx.2024.100305
- Qadir J, Wen SY, Yuan H, Yang BB. CircRNAs regulate the crosstalk between inflammation and tumorigenesis: The bilateral association and molecular mechanisms. *Mol Ther*. 2023;31(6):1514-1532. doi: 10.1016/j.ymthe.2022.12.005
- He AT, Liu J, Li F, Yang BB. Targeting circular RNAs as a therapeutic approach: Current strategies and challenges. *Signal Transduct Target Ther*. 2021;6(1):185. doi: 10.1038/s41392-021-00569-5
- Holubowicz R, Du SW, Felgner J, et al. Safer and efficient base editing and prime editing via ribonucleoproteins delivered through optimized lipid-nanoparticle formulations. *Nat Biomed Eng*. 2025;9(1):57-78. doi: 10.1038/s41551-024-01296-2
- Guo J, Gu M, Chen Y, et al. Nucleic acid delivery by lipid nanoparticles for organ targeting. *Chin Chem Lett*. 2025;110849. doi: 10.1016/j.cclet.2025.110849
- Hou X, Zaks T, Langer R, Dong Y. Lipid nanoparticles for mRNA delivery. *Nat Rev Mater*. 2021;6(12):1078-1094. doi: 10.1038/s41578-021-00358-0
- Leighton LJ, Chaudhary N, Tompkins HT, et al. The design, manufacture and LNP formulation of mRNA for research use. *Nat Protocols*. 2025;20(12):3552-3581. doi: 10.1038/s41596-025-01174-4
- Li M, Li X, He Z, et al. Delivery of GAS5 by LNP promotes tendon-bone healing in rotator cuff injury. *Bioact Mater*. 2025;51:758-773. doi: 10.1016/j.bioactmat.2025.06.009
- Ur Rehman S, Iqbal S, Shahid MU, Jahangir MS, Malik AL. Cartilage: Structure, function, and the pathogenesis of osteoarthritis. In: *Advancements in Synovial Joint Science-Structure, Function, and Beyond*. London: IntechOpen; 2024.
- Li B, Yang Z, Li Y, Zhang J, Li C, Lv N. Exploration beyond osteoarthritis:

- The association and mechanism of its related comorbidities. *Front Endocrinol (Lausanne)*. 2024;15:1352671. doi: 10.3389/fendo.2024.1352671
15. Alad M, Yousef F, Epure LM, et al. Unraveling osteoarthritis: Mechanistic insights and emerging therapies targeting pain and inflammation. *Biomolecules*. 2025;15(6):874. doi: 10.3390/biom15060874
 16. Shen Y, Xiong J, Zhang Y, Gao Z, Ding C, Lu Y. Messenger RNA therapy in bone and joint diseases: Rationale, delivery systems, and applications. *BMT*. 2025. doi: 10.12336/bmt.25.00011
 17. Kon E, Ad-El N, Hazan-Halevy I, Stotsky-Oterin L, Peer D. Targeting cancer with mRNA-lipid nanoparticles: Key considerations and future prospects. *Nat Rev Clin Oncol*. 2023;20(11):739-754. doi: 10.1038/s41571-023-00811-9
 18. Li T, Peng J, Li Q, Shu Y, Zhu P, Hao L. The mechanism and role of ADAMTS protein family in osteoarthritis. *Biomolecules*. 2022;12(7):959. doi: 10.3390/biom12070959
 19. Wang Z, Li W, Chen S, Tang XX. Role of ADAM and ADAMTS proteases in pathological tissue remodeling. *Cell Death Discov*. 2023;9(1):447. doi: 10.1038/s41420-023-01744-z
 20. Latourte A, Richette P. Inhibition of ADAMTS-5: The right target for osteoarthritis? *Osteoarthritis Cartil*. 2022;30(2):175-177. doi: 10.1016/j.joca.2021.09.012
 21. Xu Z, Ke T, Zhang Y, Guo L, Chen F, He W. Danshensu inhibits the IL-1 β -induced inflammatory response in chondrocytes and osteoarthritis possibly via suppressing NF- κ B signaling pathway. *Mol Med*. 2021;27(1):80. doi: 10.1186/s10020-021-00329-9
 22. Zhou D, Wei Y, Sheng S, et al. MMP13-targeted siRNA-loaded micelles for diagnosis and treatment of posttraumatic osteoarthritis. *Bioact Mater*. 2024;37:378-392. doi: 10.1016/j.bioactmat.2024.04.010
 23. Park H, Lee HR, Shin HJ, et al. p16INK4a-siRNA nanoparticles attenuate cartilage degeneration in osteoarthritis by inhibiting inflammation in fibroblast-like synoviocytes. *Biomater Sci*. 2022;10(12):3223-3235. doi: 10.1039/D1BM01941D
 24. Buckland J. RANKL from cartilage linked to subchondral bone loss. *Nat Rev Rheumatol*. 2012;8(8):439-439. doi: 10.1038/nrrheum.2012.110
 25. Feng T, Wu QF. A review of non-coding RNA related to NF- κ B signaling pathway in the pathogenesis of osteoarthritis. *Int Immunopharmacol*. 2022;106:108607. doi: 10.1016/j.intimp.2022.108607
 26. Catheline SE, Bell RD, Oluech LS, et al. IKK β -NF- κ B signaling in adult chondrocytes promotes the onset of age-related osteoarthritis in mice. *Sci Signal*. 2021;14(701):eabf3535. doi: 10.1126/scisignal.abf3535
 27. Warde N. Inducing tolerogenic DCs in arthritis. *Nat Rev Rheumatol*. 2011;7(8):437-437. doi: 10.1038/nrrheum.2011.92
 28. Bailey KN, Alliston T. At the crux of joint crosstalk: TGF β signaling in the synovial joint. *Curr Rheumatol Rep*. 2022;24(6):184-197. doi: 10.1007/s11926-022-01074-6
 29. Hu K, Song M, Song T, Jia X, Song Y. Osteoimmunology in osteoarthritis: Unraveling the interplay of immunity, inflammation, and joint degeneration. *J Inflamm Res*. 2025;18:4121-4142. doi: 10.2147/JIR.S514002
 30. Kong K, Li B, Chang Y, et al. Delivery of FGF18 using mRNA-LNP protects the cartilage against degeneration via alleviating chondrocyte senescence. *J Nanobiotechnology*. 2025;23(1):34. doi: 10.1186/s12951-025-03103-9
 31. Rohner E, Yang R, Foo KS, Goedel A, Chien KR. Unlocking the promise of mRNA therapeutics. *Nat Biotechnol*. 2022;40(11):1586-1600. doi: 10.1038/s41587-022-01491-z
 32. Shang X. Mechanosensitive miRNAs in cartilage and subchondral bone remodeling: Emerging targets for osteoarthritis therapy. *J Inflamm Res*. 2025;18:9609-9625. doi: 10.2147/JIR.S529149
 33. Wei W, He S, Wang Z, et al. LINC01534 promotes the aberrant metabolic dysfunction and inflammation in IL-1 β -simulated osteoarthritic chondrocytes by targeting miR-140-5p. *Cartilage*. 2021;13(2 suppl):898S-907S. doi: 10.1177/1947603519888787
 34. Chen Y, Huang H, Zhong W, Li L, Lu Y, Si HB. miR-140-5p protects cartilage progenitor/stem cells from fate changes in knee osteoarthritis. *Int Immunopharmacol*. 2023;114:109576. doi: 10.1016/j.intimp.2022.109576
 35. Liu D, Liang YH, Yang YT, et al. Circular RNA in osteoarthritis: An updated insight into the pathophysiology and therapeutics. *Am J Transl Res*. 2021;13(1):11-23.
 36. Pekáčová A, Baloun J, Švec X, Šenolt L. Non-coding RNAs in diseases with a focus on osteoarthritis. *Wiley Interdiscip Rev RNA*. 2023;14(3):e1756. doi: 10.1002/wrna.1756
 37. Liang ZJ, Tan J, Tang L, et al. NGF monoclonal antibody DS002 alleviates chemotherapy-induced peripheral neuropathy in rats. *Acta Pharmacol Sin*. 2022;43(11):2841-2847. doi: 10.1038/s41401-022-00904-8
 38. Liu S, Shen Y, Chen P, et al. Preparation and characterization of a high-affinity monoclonal antibody against nerve growth factor. *Protein Expr Purif*. 2022;189:105966. doi: 10.1016/j.pep.2021.105966
 39. Zhang J, Fan YX, Huang Y, et al. The safety, tolerability, pharmacokinetics and pharmacodynamics of single subcutaneous administration of a novel anti-NGF monoclonal antibody (AK115) in healthy participants: A randomized, double-blind, placebo-controlled, dose-escalation phase I clinical trial. *Drug Des Dev Ther*. 2025;19:3225-3235. doi: 10.2147/DDDT.S500902
 40. Tung NPH, Lim WM, Liew YK, et al. Recent advances in nanomedicine for ocular drug delivery. *BMT*. 2025. doi: 10.12336/bmt.25.00022
 41. Zhou K, Yuan M, Sun J, et al. Co-delivery of IL-1Ra and SOX9 via AAV inhibits inflammation and promotes cartilage repair in surgically induced osteoarthritis animal models. *Gene Ther*. 2025;32(3):211-222. doi: 10.1038/s41434-025-00515-y
 42. DeJulius CR, Walton BL, Colazo JM, et al. Engineering approaches for RNA-based and cell-based osteoarthritis therapies. *Nat Rev Rheumatol*. 2024;20(2):81-100. doi: 10.1038/s41584-023-01067-4
 43. Chen T, Weng W, Liu Y, Aspera-Werz RH, Nüssler AK, Xu J. Update on novel non-operative treatment for osteoarthritis: Current status and future trends. *Front Pharmacol*. 2021;12:755230. doi: 10.3389/fphar.2021.755230
 44. Zare M, Farhadi A, Zare F, et al. Genetically engineered *E. coli* invade epithelial cells and transfer their genetic cargo into the cells: An approach to a gene delivery system. *Biotechnol Lett*. 2023;45(7):861-871. doi: 10.1007/s10529-023-03387-7
 45. Harimoto T, Hahn J, Chen YY, et al. A programmable encapsulation system improves delivery of therapeutic bacteria in mice. *Nat Biotechnol*. 2022;40(8):1259-1269. doi: 10.1038/s41587-022-01244-y
 46. Nazli A, Malanga M, Sohajda T, Béni S. Cationic cyclodextrin-based carriers for drug and nucleic acid delivery. *Pharmaceutics*. 2025;17(1):81. doi: 10.3390/pharmaceutics17010081
 47. Khodaei R, Bayandori M, Sarpoli LMG, et al. Synthesis, characterization, and cellular investigation of three smart polymeric nanoparticles as efficient plasmid CRISPR (pCRISPR) delivery vehicles. *Adv Nat Sci Nanosci Nanotechnol*. 2024;15(4):045003. doi: 10.1088/2043-6262/ad6e5c
 48. Liu H, Su R, Qi W, Wang Y. Cationic polymers for gene delivery: Properties and functional optimization. *ChemBioChem*. 2025;26(10):e202500029. doi: 10.1002/cbic.202500029
 49. Thorat S, Bhattacharya S. Adrinogenic colon cancer treatment using poly(β -amino esters) (PBAEs): Mechanistic insights, advanced utilization approaches, and future directions. *J Macromol Sci B*. 2025;Part B:1-17. doi: 10.1080/00222348.2025.2495416
 50. Chen Q, Su L, He X, et al. Poly(beta-amino ester)-based nanoparticles

- enable nonviral delivery of base editors for targeted tumor gene editing. *Biomacromolecules*. 2022;23(5):2116-2125. doi: 10.1021/acs.biomac.2c00137
51. Moosavi SG, Rahiman N, Jaafari MR, Arabi L. Lipid nanoparticle (LNP) mediated mRNA delivery in neurodegenerative diseases. *J Control Release*. 2025;381:113641. doi: 10.1016/j.jconrel.2025.113641
 52. Yu X, Xu T, Shi H, et al. Cartilage-targeting mRNA-lipid nanoparticles rescue perifocal apoptotic chondrocytes for integrative cartilage repair. *Chem Eng J*. 2023;465:142841. doi: 10.1016/j.cej.2023.142841
 53. Wen M, Guo X, Zhang J, et al. Non-coding RNA in cartilage regeneration: Regulatory mechanism and therapeutic strategies. *Front Bioeng Biotechnol*. 2025;13:1522303. doi: 10.3389/fbioe.2025.1522303
 54. Zhao Z, Wang P, Li Z, et al. Targeted lipid nanoparticles distributed in hydrogel treat osteoarthritis by modulating cholesterol metabolism and promoting endogenous cartilage regeneration. *J Nanobiotechnol*. 2024;22(1):786. doi: 10.1186/s12951-024-02965-9
 55. Pontes AP, Welting TJM, Rip J, Creemers LB. Polymeric nanoparticles for drug delivery in osteoarthritis. *Pharmaceutics*. 2022;14(12):2639. doi: 10.3390/pharmaceutics14122639
 56. Cui Y, Li N, Wu J, et al. Navigating the landscape of materials-based RNA delivery systems in bone healing. *Adv Funct Mater*. 2025:e09383. doi: 10.1002/adfm.202509383
 57. Anderson CD. Therapeutic potential for mRNA-based IGF-I regenerative therapy. *Mol Ther Nucleic Acids*. 2024;35(1):102143. doi: 10.1016/j.omtn.2024.102143
 58. Liu J, Zhang Y, Liu C, et al. A single dose of VEGF-A circular RNA sustains in situ long-term expression of protein to accelerate diabetic wound healing. *J Control Release*. 2024;373:319-335. doi: 10.1016/j.jconrel.2024.07.018
 59. Cai J, Qiu Z, Chi-Shing Cho W, et al. Synthetic circRNA therapeutics: Innovations, strategies, and future horizons. *MedComm (2020)*. 2024;5(11):e720. doi: 10.1002/mco.2.720
 60. Li M, Jia X, Lai P, et al. Injectable microenvironment-responsive hydrogels encapsulating engineered NF- κ B-targeting circular RNA for osteoarthritis therapy. *J Control Release*. 2025;385:114039. doi: 10.1016/j.jconrel.2025.114039
 61. Omo-Lamai S, Zamora ME, Mueller BK, Casciano JC, Brenner JS. RNA-lipid nanoparticles for acute critical illnesses. *Nat Rev Bioeng*. 2025;3(9):775-790. doi: 10.1038/s44222-025-00314-5
 62. Sarmah S, Baidya S, De M. Recent advances in lipid nanoparticles: Nucleic acid therapeutics and targeting strategies. *Small*. 2025;21:e06812. doi: 10.1002/sml.202506812
 63. Xu S, Hu Z, Song F, Xu Y, Han X. Lipid nanoparticles: Composition, formulation, and application. *Mol Ther Methods Clin Dev*. 2025;33(2):101463. doi: 10.1016/j.omtm.2025.101463
 64. Ditto AJ, Shah PN, Yun YH. Non-viral gene delivery using nanoparticles. *Expert Opin Drug Deliv*. 2009;6(11):1149-1160. doi: 10.1517/17425240903241796
 65. Yao Z, Liu T, Wang J, et al. Targeted delivery systems of siRNA based on ionizable lipid nanoparticles and cationic polymer vectors. *Biotechnol Adv*. 2025;81:108546. doi: 10.1016/j.biotechadv.2025.108546
 66. Zhang H, Barz M. Investigating the stability of RNA-lipid nanoparticles in biological fluids: Unveiling its crucial role for understanding LNP performance. *J Control Release*. 2025;381:113559. doi: 10.1016/j.jconrel.2025.02.055
 67. Zhao X, Lin J, Liu M, et al. Targeting FAP-positive chondrocytes in osteoarthritis: A novel lipid nanoparticle siRNA approach to mitigate cartilage degeneration. *J Nanobiotechnology*. 2024;22(1):659. doi: 10.1186/s12951-024-02946-y
 68. Liu J, Liu J, Mu W, et al. Delivery strategy to enhance the therapeutic efficacy of liver fibrosis via nanoparticle drug delivery systems. *ACS Nano*. 2024;18(32):20861-20885. doi: 10.1021/acsnano.4c02380
 69. Dong C, Tan D, Sun H, et al. Interleukin-12 Delivery strategies and advances in tumor immunotherapy. *Curr Issues Mol Biol*. 2024;46:11548-11579.
 70. Joyce M, Hodgkinson T, Intini C, Dixon J, Kelly D, O'Brien F. Gene activated reinforced scaffolds for SOX9 delivery to enhance repair of large load bearing articular cartilage defects. *Eur Cells Mater*. 2024;47:91-108. doi: 10.22203/eCM.v047a07
 71. Sun M, Ma B, Pan Z, et al. Targeted therapy of osteoarthritis via intra-articular delivery of lipid-nanoparticle-encapsulated recombinant human FGF18 mRNA. *Adv Healthc Mater*. 2024;13(29):2400804. doi: 10.1002/adhm.202400804
 72. Mori Y, Saito T, Chang SH, et al. Identification of fibroblast growth factor-18 as a molecule to protect adult articular cartilage by gene expression profiling. *J Biol Chem*. 2014;289(14):10192-10200. doi: 10.1074/jbc.M113.524090
 73. Huang K, Liu X, Qin H, et al. FGF18 encoding circular mRNA-LNP based on glycerolipid engineering of mesenchymal stem cells for efficient amelioration of osteoarthritis. *Biomater Sci*. 2024;12(17):4427-4439. doi: 10.1186/s12951-025-03103-9
 74. DeJulius CR, Gulati S, Hasty KA, Crofford LJ, Duvall CL. Recent advances in clinical translation of intra-articular osteoarthritis drug delivery systems. *Adv Ther (Weinh)*. 2021;4(1):2000088. doi: 10.1002/adtp.202000088
 75. Cao X, Cai Z, Zhang J, Zhao F. Engineering circular RNA medicines. *Nat Rev Bioeng*. 2025;3(4):270-287. doi: 10.1038/s44222-024-00259-1
 76. Mazziotta C, Badiale G, Cervellera CF, Tognon M, Martini F, Rotondo JC. Regulatory mechanisms of circular RNAs during human mesenchymal stem cell osteogenic differentiation. *Theranostics*. 2024;14(1):143-158. doi: 10.7150/thno.89066
 77. Guo SK, Suo J, Huang Y, et al. Therapeutic circRNA aptamer alleviates PKR-associated osteoarthritis. *Sci Bull (Beijing)*. 2025;70(14):2232-2236. doi: 10.1016/j.scib.2025.02.027
 78. Zhao DW, Zhang J, Chen C, et al. Rejuvenation modulation of nucleus pulposus progenitor cells reverses senescence-associated intervertebral disc degeneration. *Adv Mater*. 2025;37(7):2409979. doi: 10.1002/adma.202409979
 79. Di Francesco M, Fragassi A, Pannuzzo M, Ferreira M, Brahmachari S, Decuzzi P. Management of osteoarthritis: From drug molecules to nano/micromedicines. *Wiley Interdiscip Rev Nanomed Nanobiotechnol*. 2022;14(3):e1780. doi: 10.1002/wnan.1780
 80. Zhou L, Rubin LE, Liu C, Chen Y. Short interfering RNA (siRNA)-based therapeutics for cartilage diseases. *Regen Eng Transl Med*. 2021;7(3):283-290. doi: 10.1007/s40883-020-00149-z
 81. Shi Y, Zhen X, Zhang Y, et al. Chemically modified platforms for better RNA therapeutics. *Chem Rev*. 2024;124(3):929-1033. doi: 10.1021/acs.chemrev.3c00611
 82. Zhuo Y, Luo Z, Zhu Z, et al. Direct cytosolic delivery of siRNA via cell membrane fusion using cholesterol-enriched exosomes. *Nat Nanotechnol*. 2024;19(12):1858-1868. doi: 10.1038/s41565-024-01785-0
 83. Gandek TB, van der Koog L, Nagelkerke A. A comparison of cellular uptake mechanisms, delivery efficacy, and intracellular fate between liposomes and extracellular vesicles. *Adv Healthc Mater*. 2023;12(25):2300319. doi: 10.1002/adhm.202300319
 84. Chen Y, Su YC, Roffler SR. Polyethylene glycol immunogenicity in nanomedicine. *Nat Rev Bioeng*. 2025;3:742-760. doi: 10.1038/s44222-025-00321-6
 85. Tenchov R, Sasso JM, Zhou QA. PEGylated lipid nanoparticle formulations: Immunological safety and efficiency perspective. *Bioconjug Chem*. 2023;34(6):941-960. doi: 10.1021/acs.bioconjchem.3c00174
 86. Huang H, Lou Z, Zheng S, et al. Intra-articular drug delivery systems for osteoarthritis therapy: Shifting from sustained release to enhancing penetration into cartilage. *Drug Deliv*. 2022;29(1):767-791.

- doi: 10.1080/10717544.2022.2048130
87. Rohila A, Shukla R. Recent advancements in microspheres mediated targeted delivery for therapeutic interventions in osteoarthritis. *J Microencapsul.* 2024;41(6):434-455.
doi: 10.1080/02652048.2024.2373723
 88. Singh R, Malhotra H, Jadhav K, *et al.* Intelligently actuating dual-barrier hyaluronic acid-functionalized inflammation-responsive nanohydrogel for targeted rheumatoid arthritis therapy. *ACS Appl Mater Interfaces.* 2025;17(28):40012-40034.
doi: 10.1021/acsami.5c06055
 89. Jana K, Ghosh S, Debnath B, *et al.* Recent advancements of hyaluronic acid nanoscaffolds in arthritis management. *ChemistrySelect.* 2024;9(32):e202402035.
doi: 10.1002/slct.202402035
 90. Yang Y, Zhang H. Intra-articular injection of nanomaterials for the treatment of osteoarthritis: From lubrication function restoration to cell and gene therapy. *Adv Funct Mater.* 2024;34(30):2401547.
doi: 10.1002/adfm.202401547
 91. Song S, Ma X, Li X, *et al.* Targeting a key pro-fibrotic factor S100A4 in cartilage to alleviate osteoarthritis progression and pain. *Nano Today.* 2025;63:102755.
doi: 10.1016/j.nantod.2025.102755
 92. Madry H, Kaul G, Cucchiari M, *et al.* Enhanced repair of articular cartilage defects *in vivo* by transplanted chondrocytes overexpressing insulin-like growth factor I (IGF-I). *Gene Ther.* 2005;12(15):1171-1179.
doi: 10.1038/sj.gt.3302515
 93. Guo X, Zheng Q, Yang S, *et al.* Repair of full-thickness articular cartilage defects by cultured mesenchymal stem cells transfected with the transforming growth factor β 1 gene. *Biomed Mater.* 2006;1(4):206-215.
doi: 10.1088/1748-6041/1/4/006
 94. Kim JY, Rhim WK, Lee SY, *et al.* Hybrid nanoparticle engineered with transforming growth factor β 1-overexpressed extracellular vesicle and cartilage-targeted anti-inflammatory liposome for osteoarthritis. *ACS Nano.* 2024;18(50):33937-33952.
doi: 10.1021/acsnano.4c07992
 95. Choi S, Choi H, Chung JW, Kim SH. Injectable endoplasmic-loaded lipid nanoparticles-hydrogel composite for cartilage regeneration. *Tissue Eng Regen Med.* 2025;22(4):409-424.
doi: 10.1007/s13770-024-00698-2
 96. Deng Z, Liu S. Inflammation-responsive delivery systems for the treatment of chronic inflammatory diseases. *Drug Deliv Transl Res.* 2021;11(4):1475-1497.
doi: 10.1007/s13346-021-00977-8
 97. Morici L, Jordan O, Allémann E, Rodríguez-Nogales C. Recent advances in nanocrystals for arthritis drug delivery. *Expert Opin Drug Deliv.* 2025;22(7):1031-1042.
doi: 10.1080/17425247.2025.2505758
 98. Han Y, Cao L, Li G, Zhou F, Bai L, Su J. Harnessing nucleic acids nanotechnology for bone/cartilage regeneration. *Small.* 2023;19(37):2301996.
doi: 10.1002/sml.202301996
 99. Mancino C, Franke M, Greco A, *et al.* RNA therapies for musculoskeletal conditions. *J Control Release.* 2025;377:756-766.
doi: 10.1016/j.jconrel.2024.11.057

Received: August 6, 2025

Revised: October 2, 2025

Accepted: October 9, 2025

Available online: December 9, 2025